

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 127 708 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

29.08.2001 Bulletin 2001/35

(51) Int Cl.7: **B41M 5/00**

(21) Application number: 01200518.7

(22) Date of filing: 15.02.2001

(84) Designated Contracting States:

AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR

Designated Extension States:

AL LT LV MK RO SI

- Sadasivan, Srodhar
Rochester, New York 14650-2201 (US)
- Whittaker, Patrick James
Rochester, New York 14650-2201 (US)
- Janssen, John W.
Rochester, New York 14650-2201 (US)

(30) Priority: 28.02.2000 US 513629

(71) Applicant: **EASTMAN KODAK COMPANY**
Rochester, New York 14650 (US)

(74) Representative:
Nunney, Ronald Frederick Adolphe et al
Kodak Limited,
Patents, W92-3A,
Headstone Drive
Harrow, Middlesex HA1 4TY (GB)

(72) Inventors:

- Sunderrajan, Suresh
Rochester, New York 14650-2201 (US)

(54) **Ink jet recording element**

(57) An ink jet recording element comprising a substrate having thereon an image-receiving layer comprising an inorganic, anionic pigment, an organic, anionic binder and an organic, cationic mordant, and a porous overcoat layer located over the image-receiving layer,

the porous overcoat layer comprising an inorganic pigment and an organic, anionic, binder, wherein the refractive index of the inorganic pigment in the overcoat layer is at least 0.05 refractive index units less than the refractive index of the inorganic, anionic pigment in the image-receiving layer.

EP 1 127 708 A1

Description

[0001] This invention relates to an ink jet recording element. More particularly, this invention relates to an ink jet recording element containing pigments.

[0002] In a typical ink jet recording or printing system, ink droplets are ejected from a nozzle at high speed towards a recording element or medium to produce an image on the medium. The ink droplets, or recording liquid, generally comprise a recording agent, such as a dye or pigment, and a large amount of solvent. The solvent, or carrier liquid, typically is made up of water, an organic material such as a monohydric alcohol, a polyhydric alcohol or mixtures thereof.

[0003] An ink jet recording element typically comprises a support having on at least one surface thereof an ink-receiving or image-forming layer, and includes those intended for reflection viewing, which have an opaque support, and those intended for viewing by transmitted light, which have a transparent support.

[0004] While a wide variety of different types of image-recording elements for use with ink jet devices have been proposed heretofore, there are many unsolved problems in the art and many deficiencies in the known products which have limited their commercial usefulness.

[0005] It is well known that in order to achieve and maintain photographic-quality images on such an image-recording element, an ink jet recording element must:

- Be readily wetted so there is no puddling, i.e., coalescence of adjacent ink dots, which leads to non-uniform density
- Exhibit no image bleeding
- Exhibit the ability to absorb high concentrations of ink and dry quickly to avoid elements blocking together when stacked against subsequent prints or other surfaces
- Exhibit no discontinuities or defects due to interactions between the support and/or layer(s), such as cracking, repellencies, comb lines and the like
- Not allow unabsorbed dyes to aggregate at the free surface causing dye crystallization, which results in bloom or bronzing effects in the imaged areas
- Have an optimized image fastness to avoid fade from contact with water or radiation by daylight, tungsten light, or fluorescent light

[0006] An ink jet recording element that simultaneously provides an almost-instantaneous ink dry time and good image quality is desirable. However, given the wide range of ink compositions and ink volumes that a recording element needs to accommodate, these requirements of ink jet recording media are difficult to achieve simultaneously.

[0007] Ink jet recording elements are known that employ porous or non-porous single layer or multilayer coatings that act as suitable image receiving layers on one or both sides of a porous or non-porous support. Recording elements that use non-porous coatings typically have good image quality but exhibit poor ink dry time. Recording elements that use porous coatings typically have poorer image quality but exhibit superior dry times.

[0008] US-A-5,104,730 relates to an ink jet recording sheet comprising a substrate and porous ink absorbent layers formed upon the substrate, wherein the bottom layer is pseudo-boehmite and a binder and the top layer is a fine silica powder. However, there is a problem with this element in that the top layer has to be peeled-off after printing which reduces the image optical density.

[0009] It is an object of this invention to provide an ink jet recording element that has a fast ink dry time. It is another object of this invention to provide an ink jet recording element that has good image quality. It is another object of the invention to provide an ink jet recording element that has improved gloss.

[0010] These and other objects are achieved in accordance with the invention which comprises an ink jet recording element comprising a substrate having thereon an image-receiving layer comprising an inorganic, anionic pigment, an organic, anionic binder and an organic, cationic mordant, and a porous overcoat layer located over the image-receiving layer, the porous overcoat layer comprising an inorganic pigment and an organic, anionic, binder, wherein the refractive index of the inorganic pigment in the overcoat layer is at least 0.05 refractive index units less than the refractive index of the inorganic, anionic pigment in the image-receiving layer.

[0011] The ink jet recording element of the invention provides good image quality, fast ink dry times and improved gloss.

[0012] The inorganic, anionic pigment in the image-receiving layer useful in the invention may be a kaolin clay, a calcined clay, calcium carbonate, titanium dioxide, talc or a silicate. In a preferred embodiment of the invention, the inorganic, anionic pigment used is a kaolin clay sold under the trade name Hydragloss® 92 (J.M. Huber Company). The amount of inorganic, anionic pigment used may range from 50% to 95% of the image-receiving layer.

[0013] The organic, anionic binder of either layer useful in the invention may be a styrene acrylic latex; a styrene butadiene latex, such as Styronal® BN 4606X (BASF Corp.); a poly(vinyl alcohol); a poly(vinyl acetate), such as Vinac® 884 (Air Products Inc.); a cellulosic or a polyurethane binder. In a preferred embodiment of the invention, a commercially-available styrene acrylic latex such as Acronal® S-728 (BASF Corp.) is used in the image-receiving layer. In

another preferred embodiment of the invention, a commercially-available poly(vinyl alcohol) such as Airvol® 21-205 (Air Products Inc.) is used in the overcoat layer.

[0014] The organic, anionic binder may be used in an amount of from 5% to 20% of the image-receiving layer or overcoat layer. In general, good results are obtained when the ratio of pigment to binder is from 5:1 to 8:1.

[0015] The organic, cationic mordant useful in the invention may be a polymer latex dispersion or a water-soluble polymer solution. Examples of mordants useful in the invention are disclosed in US-A-5,474,843. Other useful mordants include cationic urethane dispersions sold under the trade name Witcobond® W-213 and Witcobond® W-215 (Witco Corporation).

[0016] In a preferred embodiment of the invention, the organic, cationic mordant is:

M1: poly(N-vinyl benzyl-N-benzyl-N,N-dimethyl ammonium chloride-co-styrene-co-divinyl benzene),

M2: poly(N-vinylbenzyl-N,N,N-trimethylammonium chloride-co-ethylene glycol dimethacrylate), or

M3: poly(N-vinylbenzyl-N,N,N-trimethylammonium chloride-co-divinyl benzene).

[0017] In general, good results have been obtained when the mordant polymer is present in an amount of from 1% to 75% by weight of the image-receiving layer, preferably from 10% to 20%.

[0018] Smaller quantities of up to 10 % of other binders may also be added to the image-receiving layer such as poly(vinyl pyrrolidone) sold as Luviskol® VA-64W (BASF Corp.) or poly(vinyl pyrrolidone-co-vinyl acetate) sold as Luviquat® PQ11PN (BASF Corp.). In addition to the above major components, other additives such as pH-modifiers like nitric acid, cross-linkers, rheology modifiers, surfactants, UV-absorbers, biocides, lubricants, dyes, optical brighteners etc. may be added as needed.

[0019] As noted above, the refractive index of the inorganic pigment in the overcoat layer is at least 0.05, preferably between 0.15 and 0.25, refractive index units less than the refractive index of the inorganic, anionic pigment in the image-receiving layer. This overcoat layer is generally optically clear and causes a reduction in light scattering by the recording element. A reduction in light scattering results in superior optical density and gloss.

[0020] The inorganic pigment useful in the overcoat layer of the invention may be, for example, a silica (such as colloidal silica, fumed silica or silica gel), an alumina (an alumina oxide, an alumina hydrate or a pseudoboehmite), a calcium carbonate, a modified kaolin clay, a montmorillonite clay, a hydrotalcite clay or a laponite clay. In a preferred embodiment of the invention, the inorganic pigment is an alumina hydrate sold under the trade name Dispal® 23N4-80 (Condea Vista Company).

[0021] The amount of inorganic pigment used may range from 50% to 95% of the image-receiving layer.

[0022] The substrate may be porous such as paper or non-porous such as cellulose acetate or polyester films. The surface of the substrate may be treated in order to improve the adhesion of the image-receiving layer to the support. For example, the surface may be corona discharge treated prior to applying the image-receiving layer to the support. Alternatively, an under-coating or subbing layer, such as a layer formed from a halogenated phenol or a partially hydrolyzed vinyl chloride-vinyl acetate copolymer, can be applied to the surface of the support.

[0023] The ink jet coating may be applied to one or both substrate surfaces through conventional pre-metered or post-metered coating methods such as blade, air knife, rod, roll coating, etc. The choice of coating process would be determined from the economics of the operation and in turn, would determine the formulation specifications such as coating solids, coating viscosity, and coating speed. In a preferred embodiment, the image-receiving layer coating formulation would have a coating solids of 40-60% and a low shear (100 rpm Brookfield) viscosity of 500-2000 centiPoise. In another preferred embodiment, the overcoat layer coating formulation would have a coating solids of 20-40% and a low shear (100 rpm Brookfield) viscosity of 400-2000 centiPoise.

[0024] The image-receiving layer thickness may range from 5 to 60 µm, preferably from 10 to 30 µm. The overcoat layer thickness may range from 2 to 20 µm, preferably from 4 to 10 µm. The coating thickness required is determined through the need for the coating to act as a sump for absorption of ink solvent and the need to hold the ink near the coating surface.

[0025] After coating, the ink jet recording element may be subject to calendering or supercalendering to enhance surface smoothness. In a preferred embodiment of the invention, the ink jet recording element is subject to hot, soft-nip calendering at a temperature of 65°C and pressure of 14000 kg/m at a speed of from 0.15 m/s to 0.3 m/s.

[0026] The substrate used in the ink jet recording element of the invention may be opaque, translucent, or transparent. There may be used, for example, plain papers, resin-coated papers, various plastics including a polyester resin such as poly(ethylene terephthalate), poly(ethylene naphthalate) and poly(ester diacetate), a polycarbonate resin, a fluorine resin such as poly(tetra-fluoro ethylene), metal foil, various glass materials, and the like. The thickness of the substrate employed in the invention can be from 12 to 500 µm, preferably from 75 to 300 µm.

[0027] Ink jet inks used to image the recording elements of the present invention are well-known in the art. The ink compositions used in ink jet printing typically are liquid compositions comprising a solvent or carrier liquid, dyes or pigments, humectants, organic solvents, detergents, thickeners, preservatives, and the like. The solvent or carrier

liquid can be solely water or can be water mixed with other water-miscible solvents such as polyhydric alcohols. Inks in which organic materials such as polyhydric alcohols are the predominant carrier or solvent liquid may also be used. Particularly useful are mixed solvents of water and polyhydric alcohols. The dyes used in such compositions are typically water-soluble direct or acid type dyes. Such liquid compositions have been described extensively in the prior art including, for example, US-A-4,381,946; US-A-4,239,543 and US-A-4,781,758.

[0028] Although the recording elements disclosed herein have been referred to primarily as being useful for ink jet printers, they also can be used as recording media for pen plotter assemblies. Pen plotters operate by writing directly on the surface of a recording medium using a pen consisting of a bundle of capillary tubes in contact with an ink reservoir.

[0029] The following example further illustrates the invention.

Example 1

Control Element 1

[0030] A paper base of Nekoosa Solutions Smooth® (Georgia Pacific Co.), Grade 5128 (Carrara White®, Color 9220), basis weight 150 g/m², was coated with an image-receiving layer as described in Table 1 below (dry grams). The coating was applied onto the paper base using a wire wound Meyer rod of wire diameter 0.51 µm with a wet laydown thickness of 40 µm. The element was air dried.

[0031] The image-receiving layer contains kaolin clay (Hydragloss® 92) and styrene acrylic latex which are both predominantly anionic. The layer also contains a mordant polymer M3 which is cationic. The coating formulation thus comprises a mixture of anionic and cationic materials. To achieve a stable formulation, it is necessary to minimize the anionic charge keeping the cationic charge constant. This is achieved by adjusting the pH of the kaolin clay and styrene acrylic latex using nitric acid. In order to achieve a stable formulation, the kaolin clay and styrene acrylic latex are added to the cationic Mordant M3 and then the pH is adjusted.

Control Element 2

[0032] A portion of Control Element 1 was overcoated with an overcoat layer as described in Table 1 using a 15 ml syringe-coater with a pre-metered application rate of 6 cc/min over a 1.07 m long substrate and air dried. The overcoat formulation was kaolin clay (Digitex® 1000), dispersed in water to form a 30% solids solution, and poly(vinyl alcohol) as described in Table 1.

Element 1 of the Invention

[0033] This element is similar to Control Element 2 except that alumina hydrate is added to the overcoat layer as described in Table 1.

[0034] Following are the substituents of the layers in the above elements:

Table 1-

Substituents (Dry Grams)					
	Control Element 1	Control Element 2		Element 1 of Invention	
Substituent	Image Receiving layer	Image Receiving Layer	Overcoat Layer	Image Receiving Layer	Overcoat Layer
Kaolin clay (Hydragloss® 92) as a dry powder	100	100	--	100	--
Mordant M3 as a 15 % solids dispersion	30	30	--	30	--

Table 1- (continued)

Substituents (Dry Grams)					
	Control Element 1	Control Element 2		Element 1 of Invention	
Styrene acrylic latex (Acronal® S728) as a 50% solids dispersion	10	10	--	10	--
Nitric Acid (1N)	1.0	1.0	--	1.0	--
Kaolin Clay (Digitex® 1000) as a dry powder	--	--	100	--	--
Alumina hydrate (Dispall® 23N4-80) as a dry powder	--	--	--	--	100
Poly(vinyl alcohol) (Airvol® 21-205) as a 21 % solids dispersion	--	--	10	--	10

Refractive Index

[0035] The refractive indices of the pigments used in the Example are as follows:

Table 2

Pigment	Refractive Index
Kaolin clay (Hydragloss® 92) as a dry powder used in image-receiving layer	1.7
Kaolin Clay (Digitex® 1000) as a dry powder used in overcoat layer in Control Element 2	1.7
Alumina hydrate (Dispall® 23N4-80) as a dry powder used in overcoat layer in Element 1 of the Invention	1.5

Printing

[0036] Samples from each of the above elements were printed using a Hewlett Packard Photosmart® printer with printer settings at "photoglossy paper, best". The inks used were Hewlett Packard Photosmart® inks. A striped target was printed comprising 100% coverage of yellow, cyan, and magenta, 200% coverage for red, green, and blue, and 300% coverage for black in areas of 1 cm by 23 cm. The black stripe was tested for dry time and optical density.

Dry Time and Optical Density

[0037] Dry time, defined as the time after printing at which no ink retransfers from the printed element to a blotting sheet is observed, was measured using a blotting technique. Immediately after printing, each element was placed on a foam base, a piece of copy paper placed on top, and a weighted smooth rod was rolled over the copy paper. The copy paper was then taken off and examined for retransfer.

[0038] The results in Table 3 are given ratings from 1-5, where 1 corresponds to no transfer (fast dry time) to the copy paper, and 5 corresponds to complete transfer (the whole stripe is visible on the copy paper).

[0039] Optical density of the printed recording elements was measured using a X-Rite® model 820 transmission/reflection densitometer with status A filtration. The black stripe on the target was tested. The results are the average of three measurements.

[0040] The following results were obtained:

Table 3

Element	Dry time	Optical Density
Control 1	1	1.61
Control 2	1	1.48
Invention 1	1	2.08

[0041] The above results show that the Element 1 of the invention has a higher optical density as compared to the Control Elements 1 and 2 while maintaining a fast dry time.

Gloss

[0042] The gloss of the above recording elements was measured using a Gardner Tri-gloss meter at the 60-degree setting according to the ASTM D523 standard. The following results were obtained:

Table 4

Element	Gloss
Control 1	8.8
Control 2	9.1
Invention 1	26.5

[0043] The above results show that Element 1 of the invention had a higher gloss as compared to Control Elements 1 and 2.

Claims

1. An ink jet recording element comprising a substrate having thereon an image-receiving layer comprising an inorganic, anionic pigment, an organic, anionic binder and an organic, cationic mordant, and a porous overcoat layer located over said image-receiving layer, said porous overcoat layer comprising an inorganic pigment and an organic, anionic, binder, wherein the refractive index of said inorganic pigment in said overcoat layer is at least 0.05 refractive index units less than the refractive index of said inorganic, anionic pigment in said image-receiving layer.
2. The recording element of Claim 1 wherein said inorganic, anionic pigment in said image-receiving layer is a kaolin clay, a calcined clay, calcium carbonate, titanium dioxide, talc or a silicate.
3. The recording element of Claim 1 wherein said inorganic, anionic pigment in said image-receiving layer is a kaolin clay.
4. The recording element of Claim 1 wherein said inorganic, anionic pigment in said image-receiving layer is present in an amount of from 50% to 95% of said image-receiving layer.
5. The recording element of Claim 1 wherein each said organic, anionic binder independently is a styrene acrylic latex, a styrene butadiene latex, a poly(vinyl alcohol), or a poly(vinyl acetate).
6. The recording element of Claim 1 wherein said organic, anionic binder in said image-receiving layer is a styrene acrylic latex.
7. The recording element of Claim 1 wherein said organic, anionic binder in said image-receiving layer is present in an amount of from 5% to 20% of said image-receiving layer.
8. The recording element of Claim 1 wherein said organic, anionic binder in said overcoat layer is poly(vinyl alcohol).

9. The recording element of Claim 1 wherein said organic, anionic binder in said overcoat layer is present in an amount of from 5% to 20% of said overcoat layer.

10. The recording element of Claim 1 wherein said organic, cationic mordant is a polymer latex dispersion, a water-soluble polymer solution or a cationic urethane dispersion.

50	100
50	100
50	100
50	100



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 20 0518

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
Y	US 5 712 027 A (ALI ET AL.) 27 January 1998 (1998-01-27) * column 21, line 3 - line 11 * * column 21, line 21 - line 24 * * column 34, line 15 - line 40 *	1-10	B41M5/00
Y	EP 0 904 953 A (CANON) 31 March 1999 (1999-03-31) * page 4, line 29 - line 31 * * page 4, line 48 - line 54; claims 1,2,4 *	1-10	
Y	EP 0 869 010 A (ILFORD) 7 October 1998 (1998-10-07) * page 2, line 5 - line 8 * * page 6, line 17 - line 18 * * page 6, line 32 - line 36 *	1-10	
Y	DE 43 30 428 A (KANZAKI PAPER) 10 March 1994 (1994-03-10) * page 4, line 42 - line 44 * * page 4, line 60 - page 5, line 1 * * page 5, line 58 - line 65 * * page 16, line 47 *	1-10	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			B41M
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 8 May 2001	Examiner Magrizos, S
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.

EP 01 20 0518

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

08-05-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5712027 A	27-01-1998	US 5589269 A	31-12-1996
		US 5342688 A	30-08-1994
		AU 6130894 A	26-09-1994
		AU 6406094 A	26-09-1994
		AU 6406194 A	26-09-1994
		CA 2155741 A	15-09-1994
		CA 2155846 A	15-09-1994
		CA 2156073 A	15-09-1994
		CN 1119003 A, B	20-03-1996
		CN 1119004 A, B	20-03-1996
		CN 1119005 A	20-03-1996
		DE 69403639 D	10-07-1997
		DE 69403639 T	15-01-1998
		DE 69403640 D	10-07-1997
		DE 69403640 T	15-01-1998
		DE 69411896 D	27-08-1998
		DE 69411896 T	01-04-1999
		EP 0688265 A	27-12-1995
		EP 0688266 A	27-12-1995
		EP 0688267 A	27-12-1995
		ES 2120613 T	01-11-1998
		JP 8508453 T	10-09-1996
		JP 8507729 T	20-08-1996
		JP 8507730 T	20-08-1996
		SG 48319 A	17-04-1998
		WO 9420304 A	15-09-1994
		WO 9420305 A	15-09-1994
		WO 9420306 A	15-09-1994
EP 904953 A	31-03-1999	AU 8703198 A	15-04-1999
		CN 1212211 A	31-03-1999
		JP 11157207 A	15-06-1999
EP 869010 A	07-10-1998	DE 69700228 D	24-06-1999
		DE 69700228 T	16-12-1999
DE 4330428 A	10-03-1994	JP 6227114 A	16-08-1994
		US 5478631 A	26-12-1995

